

Handled by, department
Marina C Andersson, kb
Fire Technology
+46 10 516 52 92, marinac.andersson@sp.se

Ovacon AB
Box 64
SE-619 22 TROSA

Reaction to fire classification report

1 Introduction

This classification report defines the classification assigned to the product “SprayTec™ G” in accordance with the procedure given in EN 13501-1:2007.

2 Details of classified product

2.1 General

The product “SprayTec™ G” is defined as glass wool fibres for insulation. Its classification is valid for the following end use application:

“SprayTec™ G” is spray-applied using a two-component binder system designated “SprayTec™ Binder System”.

2.2 Product description

The product, “SprayTec™ G”, is fully described in the test reports provided in support of classification listed in Clause 3.1.

3 Test reports & test results in support of classification

3.1 Test reports

This classification is based on the test reports listed below:

Name of laboratory	Name of sponsor	Test report ref no	Accredited test method
SP	Ovacon AB	PX00008H	EN ISO 1182
SP	Ovacon AB	PX 00008-01:N	EN ISO 1716

SP Technical Research Institute of Sweden

Postal address
SP
Box 857
SE-501 15 Borås
SWEDEN

Office location
Västeråsen
Brinellgatan 4
SE-504 62 Borås
SWEDEN

Phone / Fax / E-mail
+46 10 516 50 00
+46 33 13 55 02
info@sp.se

Laboratories are accredited by the Swedish Board for Accreditation and Conformity Assessment (SWEDAC) under the terms of Swedish legislation. This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

3.2 Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance with parameters
EN ISO 1182	ΔT (°C)	5	4	Compliant
	Δm (%)		3	Compliant
	T_f (s)		0	Compliant
EN ISO 1716	PCS (MJ/kg)	3	0.58	Compliant

4 Classification and field of application

4.1 Reference and direct field of application

This classification has been carried out in accordance with clause 11 and 15 of EN 13501-1:2007.

4.2 Classification

The product called “SprayTec™ G” in relation to its reaction to fire behaviour is classified:

A1

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation product is:

Fire Behaviour	Smoke Production			Flaming Droplets		
A1	-	s	-	,	d	-

Reaction to fire classification: *A1*

4.3 Field of application:

This classification is valid for the following product parameters:


Nominal density: 45 - 55 kg/m³.

The sample was delivered by the client. SP Fire Technology was not involved in the sampling procedure.


5 Limitations

This classification document does not represent type approval or certification of the product.

SP Technical Research Institute of Sweden
Fire Technology - Fire Dynamics



Per Thureson
Technical Manager



Marina C Andersson
Technical Officer